



SMZ, a.s. Jelšava



GM I

Description and physical properties :

Sintered magnesia produced by firing, magnetic separation and screening to required parameters.

DBM FOR STEEL INDUSTRY

Chemical parameters:	
MgO (%)	min. 82,0 %
CaO (%)	max. 9,0 %
Fe₂O₃ (%)	max. 7,8 %
SiO₂ (%)	max. 1,5 %
Granulation (mm)	0 - 2 0 - 4 0 - 6 0 - 8
Bulk density (g/cm³)	According to customers requiremens.

Application	Limit of application - 1 650 °C. Suitable for basic refractories unshaped products for steelworks.
Packing	Bulk in railway wagons; Big - Bags.